

# Rotatable Magnetron Sputtering Targets



## High Purity Tungsten Metal

### KEY FEATURES

Saint-Gobain sputtering targets are produced using a proprietary process, which brings a unique set of features to the market. Our W Targets combine high-purity, continuous surface (no joints) up to 3.9 meters long (12.75 feet) and even in a customized Dog-Bone shape enabling the best material usage. The strong bond on the backing tubes (Stainless steel or Titanium) is Indium-free and allows safe operation down to the last mm of sputtering.

Purity	>99.95%
Target Thickness	Up to 15 mm
Thickness profile	Straight or Dog-bone (without joints)
Target maximum length	Up to 3.9 meters (12.75 feet)
Target density	16.8 ± 0.3 g/cm <sup>3</sup>
Oxygen Content	< 200 ppm
Surface finish (Ra)	Polished (Ra < 3.2) or Raw (to custom. choice)

### APPLICATIONS

Our high purity W Targets are proven and qualified by various end-users for the most demanding applications such as:

- Electrochromic glazing stacks (enabling WO<sub>x</sub> or HWO<sub>x</sub> layers)

### BENEFITS

- Very high purity
- Safe and Stable operation with reduced risk of micro-arcs
- Lower cost of ownership thanks to the customized “dog-bone” shape option

The information contained in this document is believed to be accurate and reliable but is presented without guarantee or warranty on the part of Saint-Gobain Ceramics and Plastics Inc. Nothing herein should be interpreted as an authorization or inducement to practice any patented invention without a license.

CoatingSolutions@Saint-Gobain.com | [www.coatingsolutions.saint-gobain.com](http://www.coatingsolutions.saint-gobain.com)